

Super Contact

POLYCHLOROPRENE BASED ADHESIVE

TECHNICAL DATA SHEET

SMART ADVANTAGES

- QUICK DRYING
- INSTANT BONDING
- BONDS A VARIETY OF MATERIALS

DESCRIPTION

Bostik Super Contact is a high quality brush grade multi-purpose Polychloroprene based contact adhesive formulated with fast crystallizing rubbers to provide high immediate bond strength with good water and heat resistance. It is formulated with a long green time to allow surfaces to be prepared and aligned prior to bonding. Bonds instantly on contact to a variety of surfaces without clamping or sustained pressure. Suitable for interior and exterior applications.



APPLICATIONS

Bostik Super Contact is ideal as a general purpose adhesive for the home where it can be used for handicrafts, shoe repair, bonding leather, decorative work, and other applications where an instant bond is required. It is extensively used in the furniture and construction industry to bond formica to chipboard, MDF and other processed boards.

ADHESION

Wood, processed boards (e.g. hardboard, supawood, chipboard, high pressure laminates, masonite, plywood), formica, veneers, floor coverings, foam, canvas, textiles, leather, felt, cloth, concrete, linoleum, glass, metal, rubber, cork and some plastics.

LIMITATIONS

- Not recommended for use as a structural adhesive.
- Not suitable for expanded polystyrene, flexible PVC, and rayon and acetate fabrics.
- Will not bond polyethylene, polypropylene, and Teflon.
- Not suitable for repair of items that hold hot liquids or where heat resistance above 70°C is required.

SAFETY INSTRUCTIONS

Bostik Super Contact is flammable. Always work in a ventilated area. Do not breathe in vapours. Avoid exposing product to any ignition sources. Do not smoke when working with Bostik Super Contact. It is advisable to wear gloves in order to avoid direct contact with the skin. If product comes in to contact with skin or eyes, rinse thoroughly and immediately with water. Seek medical attention if irritation or discomfort persists. Keep out of reach of children! Refer to our Safety Data Sheets for further toxicological information and comprehensive handling instructions.

SURFACE PREPARATION

Surfaces must be clean, dry and free from all loose materials, dust, dirt, oil, rust and any other contaminants. Non-porous substrates such as metals, glass and plastics should be degreased with a solvent. Hard plastics should be lightly abraded with emery paper. Poor surface preparation may result in a weak bond and delamination of the substrates along the glue line.



TECHNICAL DATA SHEET

HOW TO USE

- 1. Ensure that surfaces are prepared as above.
- 2. For best results, ensure that temperature of the surfaces to be bonded is above 18°C.
- 3. Stir product well before use.
- 4. Apply adhesive to both surfaces evenly with a fine serrated trowel or a stiff brush.
- 5. Allow both surfaces to dry (approximately 5 to 10 minutes under normal room temperature conditions). The adhesive should take on a uniform glossy appearance when it is dry. There should be no transfer of adhesive to the back of a finger when touched). Solvent entrapment leads to problems such as bubbling or edge lifting as the solvents try and escape.
- 6. After the surfaces are touch dry, they must be brought together before the open time or tack life is exceeded. This is the time within which a satisfactory bond can be formed under contact pressure, and is approximately 20 minutes under ambient conditions.
- 7. Ensure that the surfaces are accurately aligned before bonding, since no adjustment is possible after the adhesive films have made contact.
- 8. Apply a firm pressure to the whole surface for a few seconds to create an instantaneous bond. A pinch roller or a J roller (8cm rubber roller with metal handle) is recommended.
- 9. Full strength is achieved after 24 hours, however, bonded assemblies can be machined or trimmed immediately after bonding.

ADDITIONAL APPLICATION NOTES

- When bonding porous surfaces, e.g. chipboard edges, apply two coats. The first coat acts as a sealer to prevent excessive absorption of the second coat into the substrate.
- If working under conditions of high relative humidity (above 70%), a condition known as 'blushing' can affect solvent based contact adhesives. The 'blush' is an effect caused by rapid evaporation of solvent, which causes condensation on the surface. Blushing can be indicated by a colour change in the glue line. A clear adhesive will turn cloudy. The condensation causes a barrier between the two glue lines and must be removed before making the bond, else bonds will be weak, the laminate may bubble, and eventual delamination will occur. To avoid blushing, it is best to keep surfaces at or above room temperature during the gluing operation.
- Consult your Bostik Rep for more information on troubleshooting with contact adhesives.

CLEANING

Clean applicators and spray equipment with suitable solvents such as toluene, acetone or thinners immediately after use

STORAGE STABILITY

Bostik Super Contact has a shelf life of at least 12 months if stored in a cool (below 25°C), dry place in its original container. If the material is kept beyond the recommended shelf life, it is not necessarily unusable, but a check should be performed to observe whether the product is still workable. Ensure that the container is tightly sealed while in storage to prevent solvent evaporation.

PRODUCT PACKAGING

50ml Tubes



PJ/D181/issue 05/May 2016/Super Contact Next Revision: May 2021 Technical Data Sheet

TECHNICAL DATA SHEET

PRODUCT CHARACTERISTICS	
Туре	Neoprene / polychloroprene adhesive
Appearance	Translucent yellow liquid
Density (g/cm³)	Approximately 0.85
Odour	Mainly ketonic
Solids (%)	Approximately 23
Viscosity (cps)	Approximately 1600

TYPICAL PERFORMANCE DATA	
Application temperature	18°C to 35°C
Open / tack off time	20 minutes (ambient conditions)
Clamping pressure	2kg/cm² (30psi)
Final setting time	24 hours
Solvent resistance	Not resistant to esters, ketones, aromatic and chlorinated
	hydrocarbons
Temperature resistance	-30°C to 70°C
Water resistance	Good
Peel test (90°) (leather – chipboard)	2.9N/mm
Tensile test – (beech wood to beech wood)	2.8N/mm²
Coverage	Approx. 2m² per litre (double sided application)

DISCLAIMER

The above information is only offered as a guide to the use of this product. Furthermore, users should satisfy themselves that it is suitable for their needs. Since we have no control over the conditions under which it is used, we cannot accept responsibility for the problems caused by the use and/or application of this product.

Head Office: +27(0)21 555 7400 Beverley Close, Montague Gardens, 7441 PO Box 37008, Chempet, 7442

www.bostik.co.za

ASK A STICKY QUESTION...

www.stickyquestions.co.za
0800 222 400

